Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2019-06-20-27** **Date: 08-03-2019**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.
Agency	:	Sri.P Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.
Customer's Reference	:	EE(YNK D)E-PMT-03/W.O/121/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-03-2019
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	06-03-2019
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.95	–
2	Finess by Air permeablity method (m^2/kg,Min)	285.4	225m^2/kg, Min
3	Density (gm/cc)	3.12	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time	145 minutes	Not less than 30 minutes
6	Final Setting time	240 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2019-06-20-27** **Date: 08-03-2019**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.
Agency	:	Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.
Customer's Reference	:	EE(YNK.D)E-PMT-03/W.O/121/2018-19
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	05-03-2019
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	05-03-2019

AE-1 A.E.E AE

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 **grams**

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	244	244	1.6	98.4	90-100
3	20 mm	5432	5676	37.8	62.2	30-70
4	10 mm	4332	10008	66.7	33.3	10-35
5	4.75 mm	4654	14662	97.7	2.3	0-5
6	Pan	338	15000	100.0	0	---

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2019-06-20-27** **Date: 07-03-2019**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.
Agency	:	Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.
Customer Reference	:	EE(YNK.D)E-PMT-03/W.O/121/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-03-2019
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	05-03-2019

AE-1 A.E.E AE

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	245	245	4.9	95.1	90-100
3	10 mm	2560	2805	56.1	43.9	25-55
4	4.75 mm	2033	4838	96.8	3.2	0-10
5	Pan	162	5000	100	0	-

CIVIL PRO Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID	:	**CP-2019-06-20-27** **Date: 07-03-2019**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.
Agency	:	Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.
Customer's Reference	:	EE(YNK.D)E-PMT-03/W.O/121/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-03-2019
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	05-03-2019
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	205	526	52.6	47.4	15-34	35-59	60-79	80-100
6	300 micron	203	729	72.9	27.1	5-20	8-30	12-40	15-50
7	150 micron	191	920	92.0	8.0	0-10	0-10	0-10	0-15
8	Pan	80	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL Pro Sig..... Date..... BANGALORE

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID	:	**CP-2019-06-20-27**	**Date: 11-03-2019**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.	
Address	:	Yelahanka Sub Division, BBMP, Bangalore.	
Project Name	:	Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.	
Agency	:	Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.	
Customer's Reference	:	EE(YNK.D)E-PMT-03/W.O/121/2018-19	
Source of Sample	:	Sample supplied by Agency	
Sample Condition	:	Satisfactory	
Date of Receipt	:	09-03-2019	
Sample Type	:	Sunvik	
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.	
Date of test:	:	09-03-2019	

A.E.E

AE

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.391	512	652	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.616	528	672	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.888	544	668	20.0%	Satisfactory	Satisfactory

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	**CP-2019-06-20-27**	**Date: 16-03-2019**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.	
Address	:	Yelahanka Sub Division, BBMP, Bangalore.	
Project Name	:	Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.	
Agency	:	Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.	
Customer's Reference	:	EE(YNK.D)E-PMT-03/W.O/121/2018-19	
Source of Sample	:	Sample supplied by Agency	
Sample Condition	:	Satisfactory	
Date of Receipt	:	12-03-2019	
Sample Type /Size	:	Precast Cover Slab(100mm)	
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete	
Date of test	:	12/03/2019	

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.51	100.48	1.116	4477	80.9	18.1	16.8	21.0
2	Cover Slab-2	75.49	100.52	1.122	4475	82.3	18.4	17.1	21.4
3	Cover Slab-3	75.50	100.51	1.118	4476	81.5	18.2	16.9	21.2

Note:
The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexports@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID : CP-2019-06-20-27 **Date: 16-03-2019**

Customer : Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.

Agency : Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.

Customer's Reference : EE(YNK.D)E-PMT-03/W.O/121/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 12-03-2019

Sample Type /Size : Precast Cover Slab(250mm)

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete

Date of test : 12/03/2019

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	200.51	250.48	3.116	31570	240.9	7.6	7.1	8.9
2	Cover Slab-2	200.49	250.52	3.122	31564	242.3	7.7	7.1	8.9
3	Cover Slab-3	200.50	250.51	3.118	31567	241.5	7.7	7.1	8.9

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2019-06-20-27** **Date: 25/03/2019**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.
Agency	:	Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.
Customer's Reference	:	EE(YNK.D)E-PMT-03/W.O/121/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-03-2019
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	25/03/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	18/03/2019	25/03/2019	151.74 X 149.59 X 150.55	22699	8.676	422.1	18.6	18.6
2	Drain Bottom Slab Concrete	M20	18/03/2019	25/03/2019	150.92 X 150.21 X 150.65	22671	8.521	428.9	18.9	
3	Drain Bottom Slab Concrete	M20	18/03/2019	25/03/2019	150.55 X 150.24 X 151.88	22618	8.689	410.6	18.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL| GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2019-06-20-27 **Date: 25/03/2019**

Customer : Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.

Agency : Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.

Customer's Reference : EE(YNK.D)E-PMT-03/W.O/121/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-03-2019

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/03/2019

SL No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	18/03/2019	25/03/2019	150.84 X 150.50 X 149.62	22702	8.676	423.8	18.7	18.5
2	Drain Bottom Slab Concrete	M20	18/03/2019	25/03/2019	149.62 X 150.48 X 151.52	22514	8.521	407.2	18.1	
3	Drain Bottom Slab Concrete	M20	18/03/2019	25/03/2019	150.83 X 151.17 X 149.47	22801	8.689	430.0	18.9	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL| GEO TECHNICAL| PROJECT

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 15/04/2019

Lab ID	:	CP-2019-06-20-27
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.
Agency	:	Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.
Customer's Reference	:	EE(YNK.D)E-PMT-03/W.O/121/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-03-2019
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	15/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	18/03/2019	15/04/2019	149.37 X 151.51 X 151.84	22631	8.061	533.8	23.6	23.0
2	Drain Bottom Slab Concrete	M20	18/03/2019	15/04/2019	151.45 X 151.89 X 150.04	23003	8.532	512.2	22.3	
3	Drain Bottom Slab Concrete	M20	18/03/2019	15/04/2019	149.07 X 150.98 X 149.07	22507	8.745	519.1	23.1	

Note:
1. The results pertain to the samples received and tested.
2. All information furnished by Customer/Representative
3. Any correction in the report will make this report invalid
4. This report without prior written approval should not be reproduced or published in full or part.
5. Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2019-06-20-27

Date: 25/03/2019

Customer : Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.

Agency : Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.

Customer's Reference : EE(YNK.D)E-PMT-03/W.O/121/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-03-2019

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/03/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	18/03/2019	25/03/2019	151.57 X 149.02 X 151.91	22588	8.676	422.9	18.7	18.7
2	Drain Bottom Slab Concrete	M20	18/03/2019	25/03/2019	149.86 X 150.56 X 150.23	22564	8.521	426.8	18.9	
3	Drain Bottom Slab Concrete	M20	18/03/2019	25/03/2019	150.10 X 150.25 X 149.06	22553	8.689	417.0	18.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2019-06-20-27 **Date: 30/03/2019**

Customer : Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.

Agency : Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.

Customer's Reference : EE(YNK.D)E-PMT-03/W.O/121/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 25-03-2019

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 30/03/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	23/03/2019	30/03/2019	150.57 X 149.26 X 149.04	22474	8.676	410.5	18.3	18.5
2	Drain Side Wall Concrete	M20	23/03/2019	30/03/2019	151.21 X 149.17 X 149.46	22555	8.521	418.8	18.6	
3	Drain Side Wall Concrete	M20	23/03/2019	30/03/2019	151.77 X 151.90 X 150.39	23054	8.689	429.6	18.6	

A.E.E

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2019-06-20-27** **Date: 20/04/2019**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.
Agency	:	Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.
Customer's Reference	:	EE(YNK.D)E-PMT-03/W.O/121/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	25-03-2019
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	20/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	23/03/2019	20/04/2019	150.64 X 149.66 X 149.11	22545	8.061	538.8	23.9	23.3
2	Drain Side Wall Concrete	M20	23/03/2019	20/04/2019	151.72 X 151.92 X 151.13	23048	8.532	523.6	22.7	
	Drain Side Wall Concrete	M20	23/03/2019	20/04/2019	151.63 X 150.88 X 149.71	22878	8.745	536.0	23.4	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL| GEO TECHNICAL| PROJECT MANAGEMENT|

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-06-20-27** **Date: 30/03/2019**

Customer : Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.

Agency : Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.

Customer's Reference : EE(YNK.D)E-PMT-03/W.O/121/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 25-03-2019

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 30/03/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	23/03/2019	30/03/2019	149.70 X 151.36 X 149.26	22659	8.676	409.3	18.1	18.2
2	Drain Side Wall Concrete	M20	23/03/2019	30/03/2019	151.22 X 151.14 X 151.63	22856	8.521	412.5	18.0	
3	Drain Side Wall Concrete	M20	23/03/2019	30/03/2019	150.21 X 150.60 X 151.78	22621	8.689	415.5	18.4	

A.E.E

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2019-06-20-27 **Date: 20/04/2019**

Customer : Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements and Construction of Drains at Supreme Layout(Vinivink Shastri Layout) in Ward No:01 of Yelahanka Sub Division.

Agency : Sri.P.Ravichndra, No.562, Down Bazar Street, Yelahanka, Bangalore-560064.

Customer's Reference : EE(YNK.D)E-PMT-03/W.O/121/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 25-03-2019

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 20/04/2019

SL No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	23/03/2019	20/04/2019	151.67 X 151.92 X 149.01	23042	8.061	533.2	23.1	23.2
2	Drain Side Wall Concrete	M20	23/03/2019	20/04/2019	149.22 X 149.13 X 151.65	22254	8.532	505.0	22.7	
3	Drain Side Wall Concrete	M20	23/03/2019	20/04/2019	151.59 X 151.53 X 150.67	22971	8.745	544.5	23.7	

A.E.E

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY